

QUICK Bengalack Rett på rust Spray

Product description

Type

QUICK Bengalack Rett på rust Spray is an alkyd-based metal paint where special raw materials are added to counteract and prevent rust formation.

Features and benefits

QUICK Bengalack Rett på rust Spray is primer and topcoat in one product. The product forms a glossy, durable and hard surface that is weather resistant and has good water and chemical resistance. Particularly well suited in areas where it is difficult to reach by brush.

Recommended use

Used indoors and outdoors for surface treatment of iron and steel. Used on items such as bicycles, fences / sheepfolds, gate poles, tools, machinery, steel structures, and the like.

Product data

Packaging size	Spray can (net content about 400 ml).
Colors	Black glossy, White glossy.
Gloss level	Glossy: 90–100.
Flash point	Closed cup: -7°C (19.4°F)
VOC for Ready-for-Use Mixture	EU limit value for the product (cat. B/e): 840 g/l. The product contains max 840 g/l VOC.

Application data

Remarks

Propellant: Butane/propane.
The product is classified as extremely flammable.

Application equipment / methods

Shake vigorously for 2 min. before use. Keep the box as vertical as possible during spraying. Spray evenly and thinly at a distance of approx. 30 cm. Keep the can in motion during application. First spray in horizontal direction. After 5 min., spray in vertical direction. Repeat with approx. 5 min. intervals until desired effect. After use, turn the box upside down and spray until only propellant gas comes out.

Conditions during application

Do not paint if there is a risk of condensation or rain and wait until the film is dry.

Drying times

The drying time is affected by temperature, air humidity and film thickness.

The drying time is measured by stated values:

Relative Humidity (RH)	50 %
Air temperature	23 °C

Technical Data Sheet

QUICK Bengalack Rett på rust Spray

Substrate temperature 23 °C

Recoatable, minimum Ca 5 min
Dry to use / careful use Min. 1 hour
Excessive loads / fully cured 3– 4 weeks

Directions for use

The substrate must be clean, sound and dry.

Substrate:	Rusted steel (and new / previously painted iron and steel).
Surface preparation	Remove loose rust, loose paint, grease and other contaminants. Wash with BUTINOX Kraftvask and rinse. The substrate must be completely dry before further treatment.
Primer:	Not necessary.
Topcoat:	2 coats QUICK Bengalack Rett på rust Spray . In areas with heavy loads and in salty environment, three to four coats are recommended for optimal protection.

Storage

In storage and in transport keep the container upright. Can be stored in freezing temperatures.

Disposal of waste

Empty containers and paint residues must be delivered at community waste disposal or the nearest recycling center.



Environmental labelling

BREEAM[®] NOR The product meets the requirements of the BREEAM-NOR for the VOC and the A20 list.

Health and safety

Please observe the environmental and precautionary notices displayed on the container.

A Material Safety Data Sheet for the product has been issued.

Detailed information regarding health and safety risks and precautions for the use of this product is specified in the product's Safety Data Sheet.

First-aid measures, refer to section 4.

Handling and storage, refer to section 7.

Transport information, refer to section 14.

Regulatory information, refer to section 15.

Miscellaneous

NOBB number

This document covers the following NOBB numbers:

55808336, 55808340

NOBB module number

42169174

Contact information

Scanox AS
P.O.Box 904 Brakerøya
3002 Drammen
Norway

Tel: +47 32 24 43 00
Fax: +47 32 84 13 85
SDSscanox@scanox.no

Disclaimer

The information in this document is given to the best of Scanox' knowledge, based on laboratory testing and practical experience. Scanox' products are considered as semi-finished goods and as such, products are often used under conditions beyond Scanox' control. Scanox cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Scanox reserves the right to change the given data without further notice.

Users should always consult Scanox for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the Norwegian (Norway) version will prevail.